

### The Andhra Pradesh Mineral Development Corporation Limited

(A State Government of A.P. Undertaking)

Door No. 294/1D, 100 Feet Tadigadapa to Enikepadu Road, Kanur, Vijayawada - 521 137.
Andhra Pradesh. Tel: 0866 - 2429999, Fax: 0866 - 2429977
E-Mail: info@apmdc.ap.gov.in: Website: www.apmdc.ap.gov.in

Lr: APMDC/HO/SCM/ MSME e-Auction/M-junction/2022-23/1582 Date: 27.01.2023

To M/s.M-Junction Services Limited, 1985 (Old Number:111), Peters Road, Gopalapuram, **CHENNAI – 600086.** 

Sir,

Sub: APMDCL – E-Auction – Sale of Coal -10<sup>th</sup> E-Auction for sale of coal to MSMEs in Madhya Pradesh –Reg.

\*\*\*\*

Advert to subject cited, it is informed that, the E-Auction for the sale of Coal to MSMEs in Madhya Pradesh for quantity of **50,000 MTs** of G-6 Grade Coal (Encl: SSCL Grade Report) @ base price of **Rs.5,600/-** scheduled on **07.02.2023**.

This letter is issued with approval of VC& MD.

Thanking you,

With Regards,

M.Sudharshan Reddy,
Dy.General Manager (Mining)

### Copy to;

- 1. Office File Copy.
- 2. Tappal File Copy.

## CRP ANC)22 344



# THE SINGARENI COLLIERIES COMPANY LIMITED

### (A GOVT, COMPANY)

e-mail id: anl\_crp@scclmines.com, Phone No. 08744-230394 DISTRICT: BHADRADRI KOTHAGUDEM, STATE: TELANGANA REGIONAL ANALYTICAL LABORATORY CORPORATE, KOTHAGUDEM - 507 101



TEST REPORT

TC837122000000147F

VC & MD., APMDC

Description & Condition Of Item Repeived.

Test requested by: Test Report No:

The following Coal analysis only done by M/s. SCCL as per the procedure given in the note mentioned Coal samples were not collected by M/s. SCCL. Coal samples received in <3 mm. size

					Date of Testing	Testing					Air-Drie	Air-Dried Basis	fore	fore	fore GCV after	fore GCV after	fore GCV after	fore GCV after	Equilibrated to
No.	· · ·	Sample Particulars	Lab ID	Date of Collection	From	70	% of % of Moist Ash		% of % of Volatile Fixed Matter Carbon	_	GCV before Acid Correction (caligr)	0	Acid Correc- tion		Acid Correction % of (Cal/gr) Moist		GCV after Acid % of Correction % of Ash (Cal/gr) Moist	GCV after Acid Acid Correction % of Ash Matter carbon	GCV after Acid % of Correction % of Ash (Cal/gr) Moist
	S	SEAMVII-B/COAL SAMPLE-S1 RALK/03 22/1088 25 03 22 31.03.22 04 04.22 8975 20.19 28.89 42 17	RALK/03.22/1088	25.03.22	31.03.22	04.04.22	8,75	20.19	28.89	42.17	5561		20	5541	5541	5541	5541	5541 6.38 20.71 29.64 43.26	5541
N	- 1	SEAMVII-B/COAL SAMPLE-S2 RALK/03.22/1089 25.03.22 31.03.22 04.04.22 8.52 24.18 26.84 40.46	RALK/03.22/1089	25.03.22	31.03.22	04.04.22	8.52	24.18	26,84	40.46	5251		19	5232	5232	5232	5232	5232 6 07 24,83 27.56 41.55	5232
دري		SEAMVII-B/COAL SAMPLE-S3 RALK/03/22/1090 25:03:22 31:03:22 04:04:22 8:41 19:24 27:97 44:38	RALK/03.22/1090	25.03.22	31.03.22	04.04.22	8.41	19.24	27.97	44.38	5676	76	76 20	20 5656	20 5656	20 5656	20 5656	20 5656 6.46 19.65 28.57 45.32	20 5656
0	ote (	Note (1) Moisture & Ash as per IS: 1350 (Part 1)-1984 Reaffirmed: 2013	350 (Part 1)-1984 Re	affirmed: 20	13														

U wha Kom. (Authorised signatory)

(4). The results relate only to the items / parameters lested above (3). Equilibrated Moisture as per IS: 1350 (Part 1)-1984 Reaffirmed: 2013

(2), GCV as per IS: 1350(Part 2)-2017

Si CHEMIST ( U USHA RANI) Quality Manager

// END OF THE REPORT //

Date: 04-04-2022