



**The Andhra Pradesh Mineral Development Corporation Limited**  
(A State Government of A.P. Undertaking)

Door No. 294/1D, 100 Feet Tadigadapa to Enikepadu Road, Kanur, Vijayawada - 521 137.  
Andhra Pradesh. Tel : 0866 - 2429999, Fax: 0866 - 2429977  
E-Mail : info@apmdc.ap.gov.in : Website : www.apmdc.ap.gov.in

Lr.APMDC/HO/SCM/MSME/E-Auction/2022-23/1444 Date:21.12.2022

To  
M/s.M-Junction Services Limited,  
195 (Old Number:111), Peters Road,  
Gopalapuram, **CHENNAI - 600086.**

Sir,

Sub: APMDC- Sale of Coal- 9<sup>th</sup> E-Auction for sale of coal to MSMEs in  
Madhya Pradesh at suliyari Coal Mine-Reg..

\*\*\*

With reference to the above cited subject, it is to inform that 9<sup>th</sup> E-  
auction for sale of Coal to MSMEs in Madhya Pradesh at suliyari Coal  
Mine is scheduled on **28.12.2022** for quantity of **40,000 MTs** of G-6  
Grade (Encl: SSCL Grade Report) coal with a base price of **Rs.5,350/- per  
Metric Ton.**

This letter is issued with approval of VC&MD.

Thanking you,

With Regards,

*MSR* 21/12/22

**M.Sudharshan Reddy,**  
**Dy.General Manager(Mining)**

Encl: SSCL Grade Report



CRP/ANL/22/344



**THE SINGARENI COLLIERIES COMPANY LIMITED**  
(A GOVT. COMPANY)

**REGIONAL ANALYTICAL LABORATORY**

CORPORATE, KOTHAGUDEM - 507 101  
DISTRICT: BHADRADRI KOTHAGUDEM, STATE: TELANGANA  
e-mail id: anl\_crp@scdmines.com, Phone No. 08744-230394



TC - 8371

TEST REPORT

Date: 04-04-2022

Test Report No: TC83712200000147F  
Test requested by: VC & MD., APMDC  
Description & Condition Of Item Received: Coal samples were not collected by M/s. SCCL. Coal samples received in <3 mm. size.  
The following Coal analysis only done by M/s. SCCL as per the procedure given in the note mentioned

Sl. No.	Sample Particulars	Lab ID	Date of Collection	Date of Testing		Air-Dried Basis							Equilibrated to 60% RH at 40° C					
				From	To	% of Moist.	% of Ash	% of Volatile Matter	% of Fixed Carbon	GCV before Acid Correction (cal/gr)	Acid Correction	GCV after Acid Correction (Cal/gr)	% of Moist.	% of Ash	% of Volatile Matter	% of fixed carbon	GCV (cal/gr)	Gr.
1	SEAMVII-B/COAL SAMPLE-S1	RALK/03.22/1088	25.03.22	31.03.22	04.04.22	8.75	20.19	28.89	42.17	5561	20	5541	6.38	20.71	29.64	43.26	5685	G6
2	SEAMVII-B/COAL SAMPLE-S2	RALK/03.22/1089	25.03.22	31.03.22	04.04.22	8.52	24.18	26.84	40.46	5251	19	5232	6.07	24.83	27.56	41.55	5372	G7
3	SEAMVII-B/COAL SAMPLE-S3	RALK/03.22/1090	25.03.22	31.03.22	04.04.22	8.41	19.24	27.97	44.38	5676	20	5656	6.46	19.65	28.57	45.32	5776	G6

Note (1). Moisture & Ash as per IS: 1350 (Part 1)-1984 Reaffirmed: 2013  
(2). GCV as per IS: 1350(Part 2)-2017  
(3). Equilibrated Moisture as per IS: 1350 (Part 1)-1984 Reaffirmed: 2013  
(4). The results relate only to the items / parameters tested above.

*U. Usha Rani*  
(Authorised signatory)  
Quality Manager  
( U USHA RANI)  
Sr. CHEMIST

// END OF THE REPORT //