



The Andhra Pradesh Mineral Development Corporation Limited
(A State Government of A.P. Undertaking)

Door No. 294/1D, 100 Feet Tadigadapa to Enikepadu Road, Kanur, Vijayawada - 521 137.
Andhra Pradesh. Tel : 0866 - 2429999, Fax: 0866 - 2429977
E-Mail : info@apmdc.ap.gov.in : Website : www.apmdc.ap.gov.in

Lr: APMDC/HO/SCM/ MSME e-Auction/M-junction/2022-23/1527 Date: 12.01.2023

To
M/s.M-Junction Services Limited,
1985 (Old Number:111), Peters Road,
Gopalapuram, **CHENNAI - 600086.**

Sir,

Sub: APMDCL - E-Auction - Sale of Coal -9th E-Auction for sale of coal to MSMEs in Madhya Pradesh -Reg.

Advert to subject cited, it is informed that, the E-Auction for the sale of Coal to MSMEs in Madhya Pradesh for quantity of **50,000 MTs** of G-6 Grade Coal (Encl: SSCL Grade Report) @ base price of **Rs.5,600/-** scheduled on **18.01.2023.**

This letter is issued with approval of VC& MD.

Thanking you,

With Regards,

MS Reddy 12/1/23
M.Sudharshan Reddy,
Dy.General Manager (Mining)

Copy to;

1. Office File Copy.
2. Tappal File Copy.



CRP/ANL/22/344




THE SINGARENI COLLIERIES COMPANY LIMITED
(A GOVT COMPANY)

REGIONAL ANALYTICAL LABORATORY

CORPORATE, KOTHAGUDEM - 507 101

DISTRICT: BHADRADRI KOTHAGUDEM, STATE: TELANGANA

e-mail id: anl_crp@scclmines.com, Phone No. 08744-230394



TC - 8371

Date 04-04-2022

TEST REPORT

Test Report No
Test requested by
Description & Condition Of Item Received

TC83712200000147F
VC & MD, APMDC

Coal samples were not collected by M/s SCCL. Coal samples received in <3 mm size
The following Coal analysis only done by M/s SCCL as per the procedure given in the note mentioned

Sl No	Sample Particulars	Lab ID	Date of Collection	Date of Testing			Air-Dried Basis							Equilibrated to 60% RH at 40° C				
				From	To	% of Moist	% of Ash	% of Volatile Matter	% of Fixed Carbon	GCV before Acid Correction (cal/gr)	Acid Correction	GCV after Acid Correction (Cal/gr)	% of Moist	% of Ash	% of Volatile Matter	% of fixed carbon	GCV (cal/gr)	Gr
1	SEAMVII B/COAL SAMPLE-S1	RALK03 22/1088	25 03 22	31 03 22	04 04 22	8.75	20.19	28.89	42.17	5661	20	5541	6.38	20.71	29.64	43.26	5685	G6
2	SEAMVII B/COAL SAMPLE-S2	RALK03 22/1089	25 03 22	31 03 22	04 04 22	8.52	24.18	26.84	40.46	5251	19	5232	6.07	24.83	27.56	41.55	5372	G7
3	SEAMVII B/COAL SAMPLE-S3	RALK03 22/1090	25 03 22	31 03 22	04 04 22	8.41	19.24	27.97	44.38	5676	20	5656	6.46	19.65	28.57	45.32	5776	G8

- Note (1) Moisture & Ash as per IS 1350 (Part 1)-1984 Reaffirmed 2013
(2) GCV as per IS 1350(Part 2)-2017
(3) Equilibrated Moisture as per IS 1350 (Part 1)-1984 Reaffirmed 2013
(4) The results relate only to the items / parameters tested above

Usha Rani
(Authorised signatory)
Quality Manager
(U SHA RANI)
Sr. CHEMIST

// END OF THE REPORT //