



The Andhra Pradesh Mineral Development Corporation Limited

(A State Government of A.P. Undertaking)

Door No. 294/1D, 100 Feet Tadigadapa to Enikepadu Road, Kanur, Vijayawada - 521 137.

Andhra Pradesh. Tel : 0866 - 2429999, Fax: 0866 - 2429977

E-Mail : info@apmdc.ap.gov.in : Website : www.apmdc.ap.gov.in

Lr.APMDC/HO/SCM/MSME/E-Auction/2022/1319

Date:23.11.2022

To

M/s M-Junction Services Limited,
195 (Old No. 111) Peters Road,
Gopalapuram, Chennai - 600086.

Sir,

Sub: APMDC- sale of Coal -8th E-Auction for sale of Coal to MSME'S in Madhya Pradesh at Suliyari Coal Mine - Reg.

With reference to the above cited subject, it is to inform that 8th E-Auction for sale of Coal to MSME'S in Madhya Pradesh at Suliyari Coal Mine is scheduled on **30.11.2022** for quantity **25,000 MTs** of **G6 Grade** (Encl: SSCL Grade Report) coal with a base price of **Rs.6800/- per Metric Ton.**

This letter is issued with the approval of VC&MD.

Thanking you,

With Regards,

HSR 23/11/22


M.Sudharshana Reddy,
Dy.General Manager (Mining)

Encl: SSCL Grade Report

CAP/ANL/22/344



THE SINGARENI COLLIERIES COMPANY LIMITED
(A GOVT COMPANY)
REGIONAL ANALYTICAL LABORATORY
CORPORATE, KOTHAGUDEM - 507 101
DISTRICT: BHADRADRI KOTHAGUDEM, STATE: TELANGANA
e-mail id: anl_crp@scclmines.com, Phone No. 08744-230394



TEST REPORT

Test Report No
Test requested by
Description & Condition Of Item Received

TC83712200000147F
VC & MD. APMDC

Coal samples were not collected by M/s SCCL. Coal samples received in <3 mm size
The following Coal analysis only done by M/s SCCL as per the procedure given in the note mentioned

Date 04-04-2022

Sl No	Sample Particulars	Lab ID	Date of Collection	Date of Testing		Air-Dried Basis							Equilibrated to 60% RH at 40° C					Gr
				From	To	% of Moist	% of Ash	% of Volatile Matter	% of Fixed Carbon	GCV before Acid Correction (cal/gr)	Acid Correc- tion	GCV after Acid Correction (Cal/gr)	% of Moist	% of Ash	% of Volatile Matter	% of fixed carbon	GCV (cal/gr)	
1	SEAMVII-B/COAL SAMPLE-S1	RALK03 22/1088	25 03 22	31 03 22	04 04 22	8.75	20.19	28.89	42.17	5561	20	5541	6.38	20.71	29.64	43.26	5685	G6
2	SEAMVII-B/COAL SAMPLE-S2	RALK03 22/1089	25 03 22	31 03 22	04 04 22	8.52	24.18	26.84	40.46	5251	19	5232	6.07	24.83	27.56	41.55	5372	G7
3	SEAMVII-B/COAL SAMPLE-S3	RALK03 22/1090	25 03 22	31 03 22	04 04 22	8.41	19.24	27.97	44.38	5676	20	5656	6.46	19.65	28.57	45.32	5776	G6

- Note (1) Moisture & Ash as per IS: 1350 (Part 1)-1984 Reaffirmed 2013
(2) GCV as per IS 1350(Part 2)-2017
(3) Equilibrated Moisture as per IS 1350 (Part 1)-1984 Reaffirmed 2013
(4) The results relate only to the items / parameters tested above

Usha Rani
(Authorised signatory)
Quality Manager
(U SHA RANI)
Sr. CHEMIST

// END OF THE REPORT //