



The Andhra Pradesh Mineral Development Corporation Limited

(A State Government of A.P. Undertaking)

Door No. 294/1D, 100 Feet Tadigadapa to Enikepadu Road, Kanur, Vijayawada - 521 137

Andhra Pradesh. Tel: 0866 - 2429999 Fax: 0866 - 2429977

E-Mail : info@apmdc.ap.gov.in : Website: www.apmdc.ap.gov.in

Lr.APMDC/HO/SCM/MSME/E-Auction/2022/074

Date: 20.04.2022

To
M/s M-Junction Services Limited,
195 (Old No. 111) Peters Road,
Gopalapuram, Chennai - 600086.

Sir,

Sub: Date Confirmation of 2nd E-Auction for sale of Coal to MSME'S in Madhya Pradesh at Suliari Coal Mine - Reg.

With reference to the above cited subject, it is to inform that 2nd E-Auction for sale of Coal to MSME'S in Madhya Pradesh at Suliari Coal Mine is scheduled on **28.04.2022** for quantity **30,000 MTs** of **G6 Grade** coal (GCV range from 5500-5800 Kcal/Kg) (Encl.SCCL Grade report) with a base price of **Rs.2668/- per Metric ton** with the following terms .

- Payment period for buyers will be 7 Central Government Working days.
- The lifting period for buyers in the site will be 30 days.
- Min.50 MT bid quantity with 5 MT as multiple factor. So, that buyer who wants to place 2 trucks for 50 MT & 60MT can be fulfilled for small MSME buyers.

This letter is issued with approval of VC& MD.

Thanking you,

With Regards,

M.Sudharshan Reddy 20/04/22

M.Sudharshan Reddy,
Dy.General Manager(Mining)

Encl. SCCL Grade Report

CRP/ANL/22/344



THE SINGARENI COLLIERIES COMPANY LIMITED

(A GOVT. COMPANY)

REGIONAL ANALYTICAL LABORATORY

CORPORATE, KOTHAGUDEM - 507 101

DISTRICT: BHADRADRI KOTHAGUDEM, STATE: TELANGANA

e-mail id: anl_crp@scclmines.com, Phone No. 08744-230394



TC - 8371

TEST REPORT

Date: 04-04-2022

Test Report No:

TC83712200000147F

Test requested by:

VC & MD., APMDC

Description & Condition Of Item Received:

Coal samples were not collected by M/s. SCCL. Coal samples received in <3 mm. size.

The following Coal analysis only done by M/s. SCCL as per the procedure given in the note mentioned

Sl. No.	Sample Particulars	Lab ID	Date of Collection	Date of Testing		Air-Dried Basis							Equilibrated to 60% RH at 40° C					
				From	To	% of Moist.	% of Ash	% of Volatile Matter	% of Fixed Carbon	GCV before Acid Correction (cal/gr)	Acid Correction	GCV after Acid Correction (Cal/gr)	% of Moist.	% of Ash	% of Volatile Matter	% of fixed carbon	GCV (cal/gr)	Gr.
1	SEAMVII-B/COAL SAMPLE-S1	RALK/03.22/1088	25.03.22	31.03.22	04.04.22	8.75	20.19	28.89	42.17	5561	20	5541	6.38	20.71	29.64	43.26	5685	G6
2	SEAMVII-B/COAL SAMPLE-S2	RALK/03.22/1089	25.03.22	31.03.22	04.04.22	8.52	24.18	26.84	40.46	5251	19	5232	6.07	24.83	27.56	41.55	5372	G7
3	SEAMVII-B/COAL SAMPLE-S3	RALK/03.22/1090	25.03.22	31.03.22	04.04.22	8.41	19.24	27.97	44.38	5676	20	5656	6.46	19.65	28.57	45.32	5776	G6

Note (1). Moisture & Ash as per IS: 1350 (Part 1)-1984 Reaffirmed: 2013

(2). GCV as per IS: 1350(Part 2)-2017

(3). Equilibrated Moisture as per IS: 1350 (Part 1)-1984 Reaffirmed: 2013

(4). The results relate only to the items / parameters tested above.

U Usha Rani

(Authorised signatory)

Quality Manager

(U USHA RANI)

Sr CHEMIST

// END OF THE REPORT //