

## The Andhra Pradesh Mineral Development Corporation Limited

(A State Government of A.P. Undertaking)

Door No. 294/1D, 100 Feet Tadigadapa to Enikepadu Road, Kanur, Vijayawada - 521 137
Andhra Pradesh. Tel: 0866 - 2429999 Fax: 0866 - 2429977
E-Mail:info@apmdc.ap.gov.in: Website: www.apmdc.ap.gov.in

Lr.APMDC/HO/SCM/MSME/E-Auction/2022/166

Date: 28.04.2022

To M/s M-Junction Services Limited, 195 (Old No. 111) Peters Road, Gopalapuram, Chennai - 600086.

Sir,

**Sub**: Date Confirmation of 3<sup>rd</sup> E-Auction for sale of Coal to MSME'S in Madhya Pradesh at Suliyari Coal Mine - Reg.

\*\*\*\*\*

With reference to the above cited subject, it is to inform that 3<sup>rd</sup> E-Auction for sale of Coal to MSME'S in Madhya Pradesh at Suliyari Coal Mine is scheduled on **11.05.2022** for quantity **30,000 MTs** of **G6 Grade** coal (GCV range from 5500-5800 Kcal/Kg) (Encl.SCCL Grade report) with a base price of **Rs.2668/- per Metric ton**.

This letter is issued with approval of VC& MD.

Thanking you,

With Regards,

M.Sudharshan Reddy,

Dy.General Manager(Mining)

Encl. SCCL Grade Report

## CRP (ANC)20 ) 344



## THE SINGARENI COLLIERIES COMPANY LIMITED (A GOVT.COMPANY)

## REGIONAL ANALYTICAL LABORATORY

CORPORATE, KOTHAGUDEM - 507 101
DISTRICT: BHADRADRI KOTHAGUDEM, STATE: TELANGANA
e-mail id: anl\_crp@scclmines.com, Phone No. 08744-230394



TEST REPORT

Date: 04-04-2022

Test requested by:

Description & Condition Of Item Received:

SOME MAINT PENNING

TC837122000000147F

VC & MD., APMDC

Coal samples were not collected by M/s. SCCL. Coal sa

Coal samples were not collected by M/s. SCCL. Coal samples received in <3 mm. size.

The following Coal analysis only done by M/s. SCCL as per the procedure given in the note mentioned.

				Date of Testing	Testing				Air-Drie	Air-Dried Basis			m	quillibr	Equilibrated to 60% RH at 40° C	% RH	12	₹40°C
N S	Sample Particulars	LabID	Date of Collection	From		% of Moist	% of Ash	% of % of % of L Ash Matter Carbon		GCV before Acid Correction (cal/gr)	Acid Correc- tion	Acid Acid Acid Correction % of (Cal/gr) Moist	% of Moist	Ash	% of % of GCV Volatile fixed (cal/gr)	% of fixed carbon		GCV (cal/gr) Gr.
4	SEAMVII-BICOAL SAMPLE-S1 RALK/03:22/1088	RALK/03 22/1088	25.03.22 31.03.22 04.04.22 8.75 20.19 28.89 42.17	31.03.22	04.04.22	8.75	20.19	28.89	42.17	5561	20	5541	6.38	20.71	6.38 20.71 29.64 43.26 5685	43.26		5685 G6
2	SEAMVII-B/COAL SAMPLE-S2 RALK/03.22/1089 25.03.22 31.03.22 04.04.22 8.52 24.18 26.84 40.46	RALK/03.22/1089	25.03.22	31.03.22	04.04.22	8.52	24.18	26.84	40.46	5251	19	5232	6.07	24.83	6.07 24.83 27.56 41.55 5372	41.55		5372
ယ	3 SEAMVII-B/COAL SAMPLE-S3 RALK/03.22/1090 25.03.22 31.03.22 04.04.22 8.41 19.24 27.97 44.38	RALK/03.22/1090	25.03.22	31.03.22	04.04.22	8.41	19.24	27.97	44.38	5676	20	5656	6.46	19.65	6.46 19.65 28.57 45.32 5776 G8	45.32		5776
			1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1	The second second		The second second		Samuel Samuel Samuel	The second second		-	The state of the s		-			1	

Note (1). Moisture & Ash as per IS: 1350 (Part 1)-1984 Reaffirmed: 2013

(2). GCV as per IS: 1350(Part 2)-2017

(3). Equilibrated Moisture as per IS: 1350 (Part 1)-1984 Reaffirmed: 2013

(4). The results relate only to the items I parameters tested above.

(Authorised signatory)
Quality Manager
(U USHA RANI)
Sr CHEMIST

// END OF THE REPORT //